



PREVODOVÁ TABUĽKA AKOSTÍ ANTIKOROVÝCH MATERIÁLOV

AISI	DIN/EN	UNI	AFNOR	ČSN/STN
201	1.4372	X12CrMnNiN17-7,5	-	-
202	1.4373	X12CrMnNiN18-9,5	-	-
301	1.4310	X10CrNi18-8	Z11CN17-8	-
303	1.4305	X10CrNiS18-9	Z8CNF18-9	17 243
304	1.4301	X5CrNi18-10	Z6CN18-9	17 240
304L	1.4306	X2CrNi19-11	Z2CN18-10	17 249
309	1.4828	X6CrNi23-14	Z15CN24-13	17 251
310	1.4842	X6CrNi25-20	Z12CN25-20	17 255
316	1.4401	X5CrNiMo17-12	Z6CND17-11	17 346
316L	1.4404	X2CrNiMo17-12	Z2CND17-12	17 349
316Ti	1.4571	X6CrNiMoTi17-12	Z6CNDT17-12	17 348
321	1.4541	X6CrNiTi18-11	Z6CNT18-10	17 247, 17 248
409	1.4512	X2CrTi12	-	-
410	1.4006	X7Cr14	Z8C13FF	17 021
420	1.4021	X20Cr13	Z20C13	17 022
420F	1.4028	X30Cr13	Z30C13	17 023
430	1.4016	X8Cr17	Z8C17	17 040
430F	1.4104	X12CrMoS17	Z10CF17	17 041.2
430Ti/439	1.4510	X3CrTi17	Z4CT17	-
434	1.4113	X8CrMo17	Z8CD17-1	-
441	1.4509	X2CrTiNb18	-	-